

# **Technical data sheet TECH PLUS 2**

Industrial Universal Putty

#### **RELATED PRODUCTS**

Betox-50PC

Hardener

#### USE:

- Means of transport
- Machines and equipment

#### **PROPERTIES**

- Good filling power
- Application of thick layers is possible •
  - Good machine sanding
- Good adhesion to numerous substrates •
  - Quickly sandable
  - Very smooth surface after sanding •
- Reduced weight compared to standard putties •



## TECH PLUS 2 Technical data sheet

		09.02.2024				
SUBSTRATES						
Old paint coatings	Degrease, dry sand P220 – P240, degrease again.					
Polyester laminates	Degrease, dry sand P80 – P120, degrease again.					
Steel	Degrease, dry sand P80 – P120, degrease the substrate and apply the epoxy primer.					
Galvanised steel	Degrease, mat with an abrasive finishing pad, degrease again.					
Aluminium	Degrease, mat with an abrasive finishing pad, degrease again.					
Two-component epoxy primers	Degrease, dry sand P220 – P240, degrease again.					
Two-component acrylic primers	Degrease, dry sand P220 – P240, degrease again.					
Caution: The putty should not be applied directly on wash primers or one-component acrylic and nitrocellulose products.						
MIXING RATIO						
		Weight ratio				
	TECH PLUS 2	100 g				
	Betox-50PC	2 g				
CONTENT OF VOLATILE ORGANIC COMPOUNDS						
VOC II/B/b limit *	250 g/l					
Actual VOC content	90 g/l					
* For the ready to apply mixture compliant with Directive UE 2004/42/CE						
APPLICATION CONDITIONS						
The putty should be applied at a temperature above +10° C.						
APPLICATION						
Ð	Clean and sand the surface.					
	Degrease.					
	Mix the components thoroughly until obtaining a uniform colour.					
	Observe the required amount of hardener.					
	It is advisable to use a putty dispense ratio.	advisable to use a putty dispenser in order to obtain the appropriate component o.				
	Apply the putty. Maximum overall layer thickness: 5 mm.					



### **TECH PLUS 2**

Technical data sheet

				09.02.2024			
	4 – 6 minutes / 20°C						
CURING TIMES							
	10°C	20°C		60°C			
	60 – 90 minutes	20 – 30 minutes		10 minutes			
CAUTION: The curing times apply to the temperatures of the individual elements.							
SANDING							
	Rough		P80 – P120				
	Finish		P120 – P240				
COLOUR							
BEIGE							
EQUIPMENT CLEANING							
NC solvent							
STORAGE CONDITIONS							
Store in a dry and cool room, away from sources of fire and heat. Avoid direct exposure to sunlight.							
SHELF LIFE							
TECH PLUS 2	12 months/20 °C						
SAFETY							
See Safety Data Sheet.							
OTHER INFORMATIONS							
Registration number: 000024104.							
The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to do a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control.							