




## Technical data sheet

# FINISH

## Finishing putty

PROPERTIES		
<p>The <b>FINISH</b> putty is a finishing putty based on small fine fillers meaning it is excellent for apply in thin layers and repairing small dents and scratches. It is intended for repairing small areas and finish surface sanding prior to coating with primers. The product is sandable with fine abrasive papers resulting in a smooth surface. <b>FINISH</b> has a very good adhesion to various substrates, including galvanised steel.</p>		
SUBSTRATES		
polyester laminates	dry sand with P80-P120 and degrease again with the PLUS 780 silicone degreaser	
steel	degrease, dry sand with P80 – P120, degrease again	
galvanised steel	degrease, mat with an abrasive finishing pad and degrease again	
aluminium	degrease, mat with an abrasive finishing pad and degrease again	
two-component acrylic fillers	degrease, dry sand with P220 – P280, degrease again	
old paint coatings	degrease, dry sand with P220 – P280, degrease again	
CAUTION		
<p>Do not apply polyester putty directly on top wash primers or one-component acrylic and nitrocellulose products.</p> <p>The putty adheres to most types of galvanised steel used today.</p>		
MIXING RATIO		
	PUTTY HARDENER	Weight ratio
		100 g 2 g
APPLICATION LIFE FROM MIXING WITH THE HARDENER		
4 to 6 min at 20°C.		

DRYING TIME		
25 to 35 min at 20°C. The time can be shortened by heating for 10 minutes at a maximum of 60°C.		
COATABILITY		
Spray polyester filler, acrylic primers, epoxy primers		
APPLICATION CONDITIONS		
The minimum application temperature is +10°C		
APPLICATION		
	Clean and sand the surface	
	Degrease the surface with PLUS 780	
	Observe the required amount of hardener. Mix the components thoroughly until a uniform colour is obtained. Weight quantity of components: Add 100 g of FINISH to 2 g of Hardener. Binding time: 4 to 6 minutes at 20°C	
	Apply a layer of 1 mm max with a putty knife.	
	Wait for 25 to 35 minutes (at 20°C)	
	rough	finish
	P180-P240	P240-P320
COLOUR		
White		

<b>CONTENT OF VOLATILE ORGANIC COMPOUNDS (VOC)</b>	
VOC II/B/b limit* = 250g/l	90 g/l
*For ready to use mixture.	
<b>EQUIPMENT CLEANING</b>	
THIN 850 acrylic thinner or NC solvent.	
<b>STORAGE CONDITIONS</b>	
Store in a cool dry room, away from sources of fire and heat. Avoid direct exposure to sunlight.	
<b>SHELF LIFE</b>	
FINISH 0,25 / 0,75 / 2,0 kg	24 months/20°C
<b>SAFETY</b>	
See Safety Data Sheet.	
<b>NOTES</b>	
Intended for professional use only.	
<b>OTHER INFORMATION</b>	
<p>Registration number: 000024104</p> <p>The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to do a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control.</p>	