



Technical data sheet

THIN 890

Fade out Thinner

PROPERTIES				
THIN 890 FADE OUT THINNER – a special thinner intended for cancelling optical colour difference between the interface of the old paint coating and the new acrylic coating. The specially selected thinners allow producing a smooth transition at the clearcoat fade out zone.				
USE				
Clearcoats Acrylic topcoats				
MIXING RATIO				
Ready to use product				
VISCOSITY				
	DIN 4/20°C	10 – 12 s		
APPLICATION				
	Conventional gravity fed spray gun	Nozzle	Pressure	Distance
		1.3 – 1.4 mm	3 – 4 bar	15 – 20 cm
CAUTION: Instructions of the equipment manufacturer must be followed.	Low-pressure gravity fed spray gun	1.2 – 1.3 mm	2 bar	10 – 15 cm
PROCEDURE				
The THIN 890 fade out thinner should be applied in thin layers, in 1-2 passes, to the contact area between the old paint coating and the newly-applied coat. Two working methods may be used: Method I (recommended): apply a thin layer of the fade out thinner immediately after applying each coating of the clearcoat or topcoat. Method II: apply a thin layer of the fade out thinner immediately after applying the last coating of the clearcoat or topcoat.				
COLOUR				
Colourless				

STORAGE CONDITIONS	
Store in a cool dry room, away from sources of fire and heat. Avoid direct exposure to sunlight.	
SHELF LIFE	
THIN 890	24 months/20°C
SAFETY	
See Safety Data Sheet.	
OTHER INFORMATION	
The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to do a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control.	