



GraviTex 5000

2 IN 1 SEALANT AND CAR BODY PROTECTION

PROPERTIES

GraviTex 5000 – a product that give a strong elastic layer with stone chipping resistance. The product limits penetration by moisture to enhance anti-corrosion protection. The product protects against petrol, oils, water and salt. It has sound-absorbing and sound-proofing properties and can also be used for sealing body joints. The product is based on synthetic resins, free of asphalts or bitumen, and coatable with any acrylic coats.








TECHNICAL DATA

Nature:	Mixture of synthetic resins
Colour:	Beige, black.
Specific weight:	1,2 kg/L at 20°C
Dry film thickness:	120 µm (1 layer)
Yield:	3.5 m ² /l at 100 µm
Number of layers:	1 – 2
VOC:	VOC II/B/e limit* - 840 g/l Actual VOC - 515 g/l * For ready to use mixture acc. to EU Directive 2004/42/EC

SUBSTRATES

Process		Polyester putties	Paint OEM	Cataphoresis	Steel
	P120				√
	P240	√	√	√	
	Degreaser	√	√	√	√



APPLICATION

		 mm	 bar	 cm		
	Sealing compound	4.0	2.5 + 3.0	1 + 2 cm	1	-
	Antigravel	4.0	3.0 + 5.0	25 + 30 cm	1 + 2	0 + 10 min 20°C

Shake the container for 3 min before use!

When applying the GraviTex 5000 antigravel directly on steel, preserve the GraviTex 5000 layer with a layer of clearcoat or enamel. Do not apply on engines, transmission units and exhaust.

CURING TIMES

	Sealing compound	Antigravel
	4 h w 20°C	60 min w 20°C
	24 h	2 h

EQUIPMENT CLEANING

White spirit or NC solvent.

STORAGE CONDITIONS

Store in a cool dry room, away from sources of fire and heat.

Avoid direct exposure to sunlight.

SHELF LIFE

GraviTex 5000: 24 months/20°C

SAFETY

See the Safety Data Sheet.

OTHER INFORMATION

Registration number: 000024104.

The effectiveness of our systems results from laboratory research and many years of experience. The data contained herein meets the current knowledge about our products and their application potential. We ensure high quality, provided the user follows the instructions and the work is performed in accordance with good workmanship. It is necessary to perform a test application of the product due to its potentially different reaction with different materials. We may not be held liable for defects if the final result was affected by factors beyond our control.